



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

(11) Publication number:

**0 247 489**  
**A2**

(12)

## EUROPEAN PATENT APPLICATION

(21) Application number: **87107185.8**

(51) Int. Cl.4: **D 06 M 15/277**

(22) Date of filing: **18.05.87**

(30) Priority: **28.05.86 JP 122920/86**  
**06.10.86 JP 238535/86**

(71) Applicant: **DAIKIN INDUSTRIES, LIMITED, Umeda Center Building 4-12 Nakazaki-nishi 2-chome Kita-ku, Osaka 530 (JP)**

(43) Date of publication of application: **02.12.87**  
**Bulletin 87/49**

(72) Inventor: **Ohmori, Akira, 16-22, Yamatedai 3-chome, Ibaraki-shi Osaka-fu (JP)**  
Inventor: **Inukai, Hiroshi, 8-11-710, Showaen, Settsu-shi Osaka-fu (JP)**

(84) Designated Contracting States: **DE FR GB**

(74) Representative: **Schüler, Horst, Dr. European Patent Attorney, Kaiserstrasse 41, D-6000 Frankfurt/Main 1 (DE)**

(54) **Fluorine-containing water-repellent oil-repellent composition.**

(57) The present invention provides a fluorine-containing water- and oil-repellent composition comprising a fluorine-containing acrylate represented by the formula:



wherein X is a fluorine atom or  $-\text{CFX}^1\text{X}^2$  group (wherein  $\text{X}^1$  and  $\text{X}^2$  are the same or different and are each a hydrogen atom or fluorine atom), Y is alkylene having 1 to 3 carbon atoms,  $-\text{CH}_2\text{CH}_2\text{N}(\text{R})\text{SO}_2-$  group (wherein R is alkyl having 1 to 4 carbon atoms) or  $-\text{CH}_2\text{CH}(\text{OZ})\text{CH}_2-$  (wherein Z is a hydrogen atom or acetyl), and Rf is fluoroalkyl having 3 to 21 carbon atoms, or fluoroalkyl having 3 to 21 carbon atoms and 1 to 10 oxygen atoms in its carbon chain (wherein no two oxygen atoms are present adjacent to each other).

**EP 0 247 489 A2**

D/2951.6

FLUORINE-CONTAINING WATER-REPELLENT  
OIL-REPELLENT COMPOSITION

5 The present invention relates to fluorine-  
containing water- and oil-repellent compositions which  
exhibit good adhesion to the articles to be treated.

10 It is known that fluorine-containing polymers,  
such as some fluoroalkyl methacrylate polymers, are usable  
as water- and oil-repellent agents (see, for example,  
Examined Japanese Patent Publication SHO 47-40467).  
However, the known polymers having water- and oil-  
repellent properties have poor compatibility with the  
article to be treated and further have the problem that  
the coating of the polymer readily peels when lightly  
15 rubbed because of low adhesive strength.

The main object of the present invention is to  
provide a fluorine-containing water- and oil-repellent  
composition for giving uniform tough coatings exhibiting  
high adhesion to the article to be treated.

20 Other objects and features of the invention will  
become apparent from the following description.

The present invention provides a fluorine-  
containing water- and oil-repellent composition  
(hereinafter referred to as Composition A) comprising a  
25 fluorine-containing polymer which comprises at least 10

mole % of a fluorine-containing acrylate represented by the formula:



5 wherein X is a fluorine atom or  $-\text{CFX}^1\text{X}^2$  group (wherein  $\text{X}^1$  and  $\text{X}^2$  are the same or different and are each a hydrogen atom or fluorine atom), Y is alkylene having 1 to 3 carbon atoms,  $-\text{CH}_2\text{CH}_2\text{N}(\text{R})\text{SO}_2-$  group (wherein R is alkyl having 1 to 4 carbon atoms) or  $-\text{CH}_2\text{CH}(\text{OZ})\text{CH}_2-$  (wherein Z is a  
10 hydrogen atom or acetyl), and Rf is fluoroalkyl having 3 to 21 carbon atoms, or fluoroalkyl having 3 to 21 carbon atoms and 1 to 10 oxygen atoms in its carbon chain (wherein no two oxygen atoms are present adjacent to each other).

15 This invention further provides a fluorine-containing water- and oil-repellent composition (hereinafter referred to as Composition B) comprising a fluorine-containing polymer which comprises


(i) 10 to 90 mole % of a monomer represented by the  
20 formula:



wherein  $\text{X}^3$  is a fluorine atom, chlorine atom or  $-\text{CFX}^4\text{X}^5$  group (wherein  $\text{X}^4$  and  $\text{X}^5$  are the same or different and  
25 are each a hydrogen atom or fluorine atom), and  $\text{R}^1$  is

alkyl having 1 to 20 carbon atoms, alicyclic group,  
aromatic group or aralkyl;

(ii) 10 to 80 mole % of a monomer represented by the  
formula:




wherein  $\text{X}^6$  is a hydrogen atom or methyl, Y is alkylene  
having 1 to 3 carbon atoms,  $-\text{CH}_2\text{CH}_2\text{N}(\text{R})\text{SO}_2-$  group  
(wherein R is alkyl having 1 to 4 carbon atoms) or  
10  $-\text{CH}_2\text{CH}(\text{OZ})\text{CH}_2-$  (wherein Z is a hydrogen atom or  
acetyl), and  $\text{Rf}^3$  is fluoroalkyl having 3 to 21 carbon  
atoms or fluoroalkyl having 3 to 21 carbon atoms and 1  
to 10 oxygen atoms in its carbon chain (wherein no two  
oxygen atoms are present adjacent to each other); and  
15 (iii) 0 to 50 mole % of other copolymerizable  
ethylenically unsaturated monomer,  
the combined amount of the monomers (i) to (iii) being 100  
mole %.


We prepared various fluorine-containing acrylate  
20 polymers and checked the polymers for adhesion to  
articles, consequently finding that polymers containing a  
specific acrylate has outstanding properties for use as a  
water- and oil-repellent agent. The present invention has  
been accomplished based on this novel finding.

25 The Rf group in the fluorine-containing acrylate


(1) to be used in Composition A of the invention preferably contains a number of fluorine atoms at least twice the number of carbon atoms contained therein. More preferred examples of such Rf groups are those represented  
 5 by the formula:



wherein m is an integer of from 1 to 5, n is 0 or 1, q is an integer of from 1 to 5, and Rf<sup>1</sup> is a fluorine atom or trifluoromethyl, those represented by the formula



wherein p is an integer of from 0 to 5, and Rf<sup>1</sup> is as defined above, or those represented by the formula:



15 wherein Ph is phenylene, and Rf<sup>2</sup> is perfluoroalkyl having 5 to 15 carbon atoms.

More specific examples of monomers (1) are  
 CH<sub>2</sub>=CF-COOCH<sub>2</sub>CH<sub>2</sub>C<sub>7</sub>F<sub>15</sub>, CH<sub>2</sub>=CF-COOCH<sub>2</sub>C<sub>2</sub>F<sub>5</sub>, CH<sub>2</sub>=CF-  
 COOCH<sub>2</sub>C<sub>8</sub>F<sub>16</sub>CF(CF<sub>3</sub>)<sub>2</sub>, CH<sub>2</sub>=CF-COOCH<sub>2</sub>-CF(CF<sub>3</sub>)OCF<sub>2</sub>-  
 20 CF(CF<sub>3</sub>)OC<sub>3</sub>F<sub>7</sub>, CH<sub>2</sub>=CF-COOCH<sub>2</sub>-CF(CF<sub>3</sub>)OC<sub>3</sub>F<sub>7</sub>, CH<sub>2</sub>=CF-  
 COOCH<sub>2</sub>CH<sub>2</sub>-N(CH<sub>3</sub>)SO<sub>2</sub>C<sub>8</sub>F<sub>17</sub>, CH<sub>2</sub>=CF-COOCH<sub>2</sub>CH(OH)CH<sub>2</sub>C<sub>9</sub>F<sub>19</sub> and  
 the like.

Examples of monomers, other than the fluorine-  
 containing acrylate (1), which can be incorporated into  
 25 the fluorine-containing polymer used in Composition A are

monomers represented by the formula:



5 wherein A is a hydrogen atom, chlorine atom or methyl and B is alkyl having 1 to 10 carbon atoms, fluoroalkyl having 1 to 10 carbon atoms, or alicyclic group having 6 to 8 carbon atoms. Also useful are other ethylenically unsaturated monomers including ethylene, propylene,  
10 styrene, and acrylates and methacrylates which have a functional group such as vinyl, hydroxyl, carboxyl, glycidyl, dialkylamino or trialkoxysilyl.

Examples of acrylates or methacrylates having a functional group are  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2\text{CH}_2\text{O})_{10}\text{COC}(\text{CH}_3)=\text{CH}_2$ ,  
15  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_{10}\text{COC}(\text{CH}_3)=\text{CH}_2$ ,  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOCH}_2\text{CH}-(\text{OCOC}(\text{CH}_3)=\text{CH}_2)\text{CH}_2\text{OCOC}(\text{CH}_3)=\text{CH}_2$ ,  $\text{CH}_2=\text{CHCOOCH}_2\text{CH}_2\text{OH}$ ,  $\text{CH}_2=\text{CHCOO-R}^A$  (wherein  $\text{R}^A$  is glycidyl),  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO-CH}_2\text{CH}_2\text{CH}_2\text{Si}(\text{OCH}_3)_3$ , etc.

More specific examples of monomers (2) are  
20  $\text{CH}_2=\text{CHCOOCH}_3$ ,  $\text{CH}_2=\text{CHCOOC}_{12}\text{H}_{25}$ ,  $\text{CH}_2=\text{CHCOO-R}^B$  (wherein  $\text{R}^B$  is cyclohexyl),  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOCH}_3$ ,  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOC}_8\text{H}_{17}$ ,  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOCH}_2\text{CH}_2\text{C}_7\text{F}_{15}$ ,  $\text{CH}_2=\text{C}(\text{Cl})\text{COOCH}_3$ , etc.

The fluorine-containing polymer to be used for Composition A is usually in the range of from 10,000 to  
25 4,000,000 in number average molecular weight (as measured

by gel permeation chromatography) and in the range of from 0.25 to 2.0, in intrinsic viscosity  $[\eta]$  (as measured at a temperature of 35°C using m-xylene hexafluoride, methyl ethyl ketone, chloroform, 1,1,1-trichloromethane or like solvent). If the molecular weight is too small, the resulting coating has low strength and is liable to peel off the article treated, whereas if it is too great, the resulting composition is difficult to apply to articles owing to increased viscosity or low free-flowing properties.

The fluorine-containing polymer used in Composition A and comprising 10 to 90 mole % of a fluorine-containing acrylate (1), especially such an acrylate wherein X is a fluorine atom, exhibits high adhesion to the article to be treated, forming a tough and flexible coating.

The monomers represented by the formula (2) and inexpensive monomers, such as ethylene, propylene and styrene, are useful for reducing the cost of the fluorine-containing polymer and act to impart hardness to the fluorine-containing polymer. The monomers of the formula (2) and other monomers, such as ethylene, propylene and styrene, are used usually in an amount of up to 90 mole %.

The fluorine-containing polymer, when containing a functional group, exhibits improved adhesion to the

article to be treated. Further the functional group can be utilized for crosslinking the fluorine-containing polymer. For the crosslinking, methods which are usually used in the art can be resorted to (see, for example,

5 Unexamined Japanese Patent Publication SHO 47-42880). Usually up to 30 mole % of acrylate or methacrylate is used which has the functional group to be introduced into the fluorine-containing polymer.



Composition B comprising a fluorine-containing  
10 polymer which comprises 10 to 90 mole % of monomer represented by the formula (3), 10 to 80 mole % of monomer represented by the formula (4) and 0 to 50 mole % of other copolymerizable ethylenically unsaturated monomer also exhibits excellent water- and oil-repellent propoerties.

15 Examples of groups  $R^1$  in the formula (3), which are not limited specifically, are alkyl groups such as methyl, ethyl, butyl and stearyl; halogenated (but not fluorinated) alkyl groups such as 2-chloroethyl; cycloalkyl groups such as cyclohexyl, bornyl and  
20 adamantyl; aromatic groups such as phenyl and naphthyl; silicon-containing groups such as trimethylsilyl and trimethylsilylpropyl; phosphorus-containing groups such as dimethylphosphateethyl; groups having an unsaturated bond such as allyl; groups having a functional group, such as  
25 cyanoethyl and glycidyl; groups having dialkylamino such




as dimethylaminoethyl; groups having an ether group such as tetrahydrofurfuryl; etc.


More specific examples of monomers (3) are



15 The  $\text{Rf}^3$  group in the fluorine-containing  
 acrylate (4) to be used in Composition B in the invention  
 preferably contains a number of fluorine atoms at least  
 twice the number of carbon atoms contained therein. More  
 preferred examples of such  $\text{Rf}^3$  groups are those  
 20 represented by the formula:



wherein  $m$  is an integer of from 1 to 5,  $n$  is 0 or 1,  $q$  is  
 an integer of from 1 to 5, and  $\text{Rf}^4$  is a fluorine atom or  
 trifluoromethyl, those represented by the formula



wherein p is an integer of from 0 to 5, and Rf<sup>4</sup> is as defined above, or those represented by the formula:







wherein Ph is phenylene, and Rf<sup>5</sup> is perfluoroalkyl having 5 to 15 carbon atoms.

More specific examples of monomer (4) include

10  $\text{CH}_2=\text{CHCOOCH}_2\text{CH}_2\text{C}_7\text{F}_{15}$ ,  $\text{CH}_2=\text{CHCOOCH}_2\text{C}_2\text{F}_5$ ,  $\text{CH}_2=\text{C}(\text{CH}_3)\text{-COOCH}_2\text{C}_8\text{F}_{16}\text{CF}(\text{CF}_3)_2$ ,  $\text{CH}_2=\text{CHCOOCH}_2\text{CF}(\text{CF}_3)\text{OCF}_2\text{CF}(\text{CF}_3)\text{OC}_3\text{F}_7$ ,  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOCH}_2\text{CF}(\text{CF}_3)\text{OC}_3\text{F}_7$ ,  $\text{CH}_2=\text{CHCOOCH}_2\text{-CH}_2\text{N}(\text{CH}_3)\text{CO}_2\text{C}_8\text{F}_{17}$ ,  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOCH}_2\text{CH}(\text{OH})\text{CH}_2\text{C}_9\text{F}_{19}$ ,  $\text{CH}_2=\text{CHCOOCH}_2\text{CH}_2\text{C}_8\text{F}_{19}$ ,  $\text{CH}_2=\text{CHCOOCH}_2\text{CF}(\text{CF}_3)\text{OC}_3\text{F}_7$ ,  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOCH}_2\text{CH}_2\text{C}_7\text{F}_{15}$  and the like.

15 Examples of copolymerizable ethylenically unsaturated monomers, other than the monomers (3) and (4), which can be incorporated into the fluorine-containing polymer in Composition B include acrylates and methacrylates having a functional group such as vinyl,

20 hydroxyl, carboxyl, glycidyl, dialkylamino or trialkoxysilyl,  $\text{CH}_2=\text{CH}_2$ ,  $\text{CH}_2=\text{CH}$  ,  $\text{CH}_2=\text{CHCH}_3$ ,  $\text{CH}_2=\text{CHCOOCH}_3$ ,  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOCH}_3$ ,  $\text{CH}_2=\text{CHCOO}$  ,  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}$  ,  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOC}_{18}\text{H}_{37}$ ,  $\text{CH}_2=\text{CHCOOC}_{12}\text{H}_{25}$ ,  $\text{CH}_2=\text{CHCOO}$  , etc.

The fluorine-containing polymer to be used for

25 Composition B is usually in the range of from 10,000 to

4,000,000 in number average molecular weight (as measured by gel permeation chromatography) and in the range of from 0.25 to 3.0, preferably from 0.5 to 2.0, in intrinsic viscosity  $[\eta]$  (as measured at a temperature of 35°C using m-xylene hexafluoride, methyl ethyl ketone, chloroform, 1,1,1-trichloromethane or like solvent). If the molecular weight is too small, the resulting coating has low strength and is liable to peel off the article treated, whereas if it is too great, the resulting composition is difficult to apply to articles owing to increased viscosity or low free-flowing properties.

The fluorine-containing polymer used in Composition B and comprising 10 to 90 mole % of an fluorine-containing acrylate (3), especially such an acrylate wherein  $X^3$  is a fluorine atom or chlorine atom exhibits high adhesion to the article to be treated, forming a tough and flexible coating.

Composition B comprising a fluorine-containing copolymer containing 10 to 80 mole % of an acrylate (4) gives a coating excellent in water- and oil-repellent properties.

Other copolymerizable ethylenically unsaturated monomer, when incorporated into composition B, acts to impart improved hardness to the coating of composition.

The fluorine-containing polymers of the present

invention can be prepared by radical polymerization (e.g. solution, bulk or emulsion polymerization) or anionic polymerization.

Examples of solvents useful for solution  
5 polymerization are fluorine-containing solvents such as m-xylene hexafluoride and trichlorotrifluoroethane, hydrocarbon solvents such as ethyl acetate, methyl isobutyl ketone, acetone, toluene and xylene, etc. The polymer obtained by solution polymerization can be used in  
10 the form of a solution which is prepared by separating the polymer from the solvent and dissolving the polymer in a solvent after drying, or in the form of a solution which is prepared by merely diluting the resulting reaction mixture.

15 The polymer obtained by bulk polymerization is usable as dissolved in a solvent after drying.

Examples of polymerization initiators useful for solution polymerization and bulk polymerization are azo compounds such as azobisisobutyronitrile, peroxide  
20 compounds such as benzoyl peroxide and the like.

For solution polymerization and block polymerization, mercaptans such as laurylmercaptan and thiophenol are usable as chain transfer agents.

In either of these two processes, the  
25 polymerization temperature is preferably 30 to 100°C.

Before application to the article to be treated, the fluorine-containing polymer prepared by solution or bulk polymerization is dissolved in a dissolving solvent capable of thoroughly dissolving the polymer and further  
5 diluting the solution with a diluting solvent capable of dissolving the polymer without permitting the dissolved polymer to separate out. Like usual water- and oil-repellent agents, the resulting composition is applied to the article by dipping, brushing, spraying or otherwise.  
10 Preferably the concentration of the composition is 0.1 to 30 wt.% for brush coating or about 0.05 to about 2 wt.% for spray coating. The coating is dried at room temperature to 150°C.

Examples of useful dissolving solvents are  
15 fluorine-containing solvents such as m-xylene hexafluoride and trichlorotrifluoroethane, chlorine-containing solvents such as trichloroethane, etc. Examples of useful diluting solvents are chlorine-containing solvents such as tetra-  
chloroethylene and trichloroethylene, ketone solvents such  
20 as acetone, ester solvents such as ethyl acetate, aromatic solvents such as toluene, etc. The dissolving solvent is usable also as the diluting solvent.

Nonionic compounds are desirable as emulsifiers for emulsion polymerization, while cationic emulsifiers  
25 are also usable.

The polymerization initiator to be used for emulsion polymerization is preferably a water-soluble compound. Examples of such compounds are azo compounds such as azobisisobutyroamide hydrochloride, peroxide compounds such as succinic acid peroxide, etc. The emulsion polymerization temperature is preferably 30 to 100°C.

The fluorine-containing polymer prepared by emulsion polymerization is usable as an aqueous composition. Usually, the emulsifier need not be removed from the reaction mixture. The aqueous water- and oil-repellent composition is usable in the same manner as above. Since the aqueous composition contains water, it is desirable to heat the coating thereof at 100 to 150°C for drying.

When the fluorine-containing acrylate of the formula (1) wherein X is trifluoromethyl is to be singly polymerized, it is preferable to resort to anionic polymerization in view of the velocity of polymerization.

Examples of polymerization initiators usable for anionic polymerization are alkali metals, metallic hydrides, sodium amide, Grignard reagents, metal alkyl, pyridine and the like.

Examples of solvents usable for anionic polymerization are aromatic solvents such as toluene,

ether solvents such as tetrahydrofuran, etc.

Anionic polymerization is conducted usually in a high vacuum of about  $1 \times 10^{-6}$  mm Hg or in a dry inert gas atmosphere. The polymerization temperature is usually  
5 -100 to 70°C.

The polymer prepared by anionic polymerization can be applied to the article to be treated in the same manner as the one prepared by solution polymerization.

The water- and oil-repellent composition of the  
10 present invention is usable for giving water- and oil-repellent properties to various solid articles which must be resistant to abrasion, such as tents, sheet covers, umbrellas, raincoats, shoes, caps to hats, bags, jackets, jumpers, aprons, blazers, slacks, skirts, other garments,  
15 carpets, sofas, curtains, etc. Further, the composition of the invention is useful as an agent for preventing the adhesion of liquid polymers such as epoxy resin.

The water- and oil-repellent composition of the invention comprises a polymer which contains as a  
20 component thereof a specific fluorine-containing acrylate having a fluorine atom or fluorine-containing group at the  $\alpha$ -position. The present composition is superior to conventional water- and oil-repellent compositions in adhesion to the article to be treated and has high  
25 durability against laundry.

Example 1

Into a 200-c.c. glass ampule were placed 50 g of a monomer represented by the formula:  $\text{CH}_2=\text{CF}-\text{COOCH}_2-\text{CF}(\text{CF}_3)\text{OC}_3\text{F}_7$  (hereinafter referred to as " $\alpha\text{F}_6\text{FO}$ "), 4 g of glycidyl methacrylate (hereinafter referred to as "GMA"), 80 g of m-xylene hexafluoride (hereinafter referred to as "m-XHF") and 0.5 g of azobisisobutyronitrile, and the mixture was deaerated and purged with nitrogen repeatedly three times by the freeze-thaw method using methanol/dry ice. The ampule was then sealed off.

The ampule was immersed in a constant-temperature bath at 50°C for 30 hours.

The reaction mixture was thereafter placed into petroleum ether, and the resulting precipitate of fluorine-containing polymer was dried, giving 52 g of a fluorine-containing polymer.

The polymer had an intrinsic viscosity  $[\eta]$  of 1.12 as measured at a temperature of 35°C using m-XHF as a solvent.

Elementary analysis of the polymer revealed 30.2% of carbon and 54.4% of fluorine, indicating that the monomers had been polymerized almost entirely.

The polymer was dissolved in m-XHF (dissolving solvent) to a concentration of 30 wt.%, and the solution was diluted with trichlorotrifluoroethane (diluting



solvent) to a concentration of 0.5 wt.%.

The dilution was applied to a synthetic leather comprising a polyurethane-coated nonwoven fabric, 3 mm in thickness, with a brush and then heated at 80°C for 30 minutes to prepare a specimen for testing adhesion.

The contact angle of water, as well as n-hexadecane, with respect to the specimen was measured immediately after the preparation and after flexing the specimen through 120 degrees 10,000 times. Table 2 shows the results.

Examples 2-9 and Comparative Examples 1-3

Adhesion test specimens were prepared in the same manner as in Example 1 using the monomers, polymer dissolving solvent and diluting solvent listed in Table 1 for each polymer. Table 2 shows the results.

20

25

Table 1-(1)

Example	Monomers and wt. ratio	[ $n$ ]	Dissolving solvent	Diluting solvent
2	$\alpha$ F6FO/MA/GMA= 66/30/4	0.98	m-XHF	Trichloro- ethane
3	$\alpha$ F6FO/MA/GMA= 50/46/4	0.90	m-XHF	Trichloro- ethane
4	$\alpha$ F6FO/MA/GMA= 28/77/5	0.91	m-XHF	Trichloro- ethane
5	$\alpha$ F17F/CMS= 70/30	0.58	Trichloro- trifluoro- ethane	Trichloro- trifluoro- ethane
6	$\alpha$ F17F/GMA= 90/10	0.62	m-XHF	Trichloro- trifluoro- ethane
7	$\alpha$ F17F/SA/17FA/ GMA=50/20/25/5	0.71	m-XHF	Trichloro- trifluoro- ethane
8	$\alpha$ F119F/MA/GMA 70/28/2	0.85	m-XHF	Trichloro- trifluoro- ethane
9	$\alpha$ F119F/EGMA/MA/ SMA=25/2/58/15	0.41	Trichloro- ethane	Trichloro- trifluoro- ethane

Table 1-(2)

Comp. Ex.	Monomers and wt. ratio	$[\eta]$	Dissolving solvent	Diluting solvent
1	17FMA/SA/GMA= 50/45/5	0.35	Trichloro- ethane	Trichloro- trifluoro- ethane
2	17FA/GMA= 90/10	0.32	m-XHF	Trichloro- trifluoro- ethane
3	19FA/MA/GMA= 65/30/5	0.28	m-XHF	Trichloro- trifluoro- ethane

In Table 1 and in the following, the monomer representing symbols represent the following.

MA	: $\text{CH}_2=\text{CHCOOCH}_3$
$\alpha\text{F17F}$	: $\text{CH}_2=\text{CFCOOCH}_2\text{CH}_2(\text{CF}_2\text{CF}_2)_3\text{CF}_2\text{CF}_3$
CMS	: $\text{CH}_2=\text{CH}-\text{Ph}-\text{CH}_2\text{Cl}$ (wherein Ph is phenylene)
SA	: $\text{CH}_2=\text{CHCOOC}_{18}\text{H}_{37}$
17FA	: $\text{CH}_2=\text{CHCOOCH}_2\text{CH}_2\text{C}_8\text{F}_{17}$
$\alpha\text{Fi19F}$	: $\text{CH}_2=\text{CFCOOCH}_2\text{CH}_2(\text{CF}_2\text{CF}_2)_3\text{CF}(\text{CF}_3)_2$
EGMA	: $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2\text{CH}_2\text{O})_3\text{COC}(\text{CH}_3)=\text{CH}_2$
SMA	: $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOC}_{18}\text{H}_{37}$
17FMA	: $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOCH}_2\text{CH}_2\text{C}_8\text{F}_{17}$
19FA	: $\text{CH}_2=\text{CHCOOCH}_2\text{CH}_2\text{C}_9\text{F}_{19}$

Table 2

		Contact angle (deg) As prepared/after flexing	
		Water	n-Hexadecane
Example 1		110/108	74/52
"	2	111/105	74/56
"	3	120/101	71/50
"	4	116/100	66/48
"	5	123/110	80/58
"	6	122/115	80/52
"	7	120/105	78/49
"	8	108/102	75/50
"	9	110/100	70/45
Comp.Ex.1		102/73.6	68/15
"	2	108/70	69/20
"	3	106/71	69/19

Example 10

Water (1.9 liters), 400 g of acetone, 300 g of  $\alpha$ -F6FO, 19 g of MA, 1 g of EGMA and 40 g of an emulsifier (K220, product of Nippon Oils & Fats Co., Ltd.) were placed into a 3-liter four-necked flask equipped with a stirrer, thermometer, reflux condenser and dropping funnel and oxygen was removed from the system by introducing nitrogen thereinto. The flask was placed into a constant-

temperature bath at 65°C. After the mixture was heated to a constant temperature, 0.1 liter of water having dissolved therein 1.6 g of azobisisobutyronitrile hydrochloride was added dropwise to the mixture to start  
5 polymerization.

Four hours later, a dispersion was obtained which contained 12 wt.% of solids. A portion of the dispersion was sampled and checked for monomer composition ratio and intrinsic viscosity  $[\eta]$ . The  $\alpha$ F6FO/MA/EGMA  
10 ratio was 97.3/6/0.3 by weight (elementary analysis: 39.6% carbon and 55.0% fluorine) and the viscosity  $[\eta]$  was 0.68.

The dispersion was diluted with water to a concentration of 0.5 wt.% in a padding container. A polyester fabric was dipped in the padding bath, squeezed  
15 to remove the dilution, then dried at 80°C for 3 minutes and heat-treated at 150°C for 3 minutes to obtain a test specimen.

The specimen was tested for water repellency according to JIS L 1092 and for oil-repellency according  
20 to AATCC 118-1966T. The results were 100<sup>+</sup> and No.6, respectively.

The same specimen as above was washed under the conditions of bath ratio of 1:50 and temperature of 40°C using a household electric washing machine and a detergent  
25 ("Super-Sabu", product of Kao Co., Ltd., Japan), then

dried in air, lightly ironed at 140°C and subjected to the two tests againing, giving the results of 100<sup>+</sup> and No.5, respectively.

Comparative Example 4

5                    Polymerization was conducted and a test specimen was prepared under the same conditions as in Example 10 with the exception of using 300 g of 17FA, 19 g of MMA and 1 g of EGMA as monomers. The polymer obtained was 0.38 in intrinsic viscosity  $[\eta]$ .

10                   Under the same conditions as in Example 10, the specimen was tested for water repellency and for oil repellency before and after laundry. The water repellency reduced from 100<sup>+</sup> to 70, and the oil repellency from No.3 to No.0.

15

Example 11

                  Into a 200-c.c. glass ampule were placed 30 g of a monomer represented by the formula:  $\text{CH}_2=\text{CClCOOCH}_3$ , 20 g of a monomer of the formula:  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COOCH}_2\text{CH}_2\text{C}_8\text{F}_{17}$ , 2 g of glycidyl methacrylate and 0.3 g of azobisisobutyronitrile, and the mixture was deaerated and purged with nitrogen repeatedly three times by the freeze-thaw method using methanol dry ice. The ampule was thereafter sealed off and immersed in a constant-temperature bath for 24 hours.

25

                  The reaction mixture was dissolved in 100 g of

chloroform, and the mixture was placed into 2 liters of petroleum ether. The resulting precipitate was dried, giving 48 g of a fluorine-containing copolymer. The copolymer had an intrinsic viscosity  $[\eta]$  of 1.06 as measured at a temperature of 35°C using chloroform as a solvent. Elementary analysis of the polymer revealed 37.4% of carbon, 17% of chlorine and 23.3% of fluorine, indicating that the monomers had been polymerized almost wholly.

10           The polymer was dissolved in chloroform (dissolving solvent) to a concentration of 5 wt.%, and the solution was diluted with 1,1,2-trichloro-1,2,2-trifluoroethane (diluting solvent) to a concentration of 0.5 wt.%.

          Using the dilution, a specimen was prepared and tested for adhesion in the same manner as in Example 1. Table 4 shows the results.

Examples 12-15 and Comparative Example 5

          Adhesion test specimens were prepared in the same manner as in Example 11 using the monomers, dissolving solvent and diluting solvent listed in Table 3 for each polymer. The specimens were similarly tested with the results given in Table 4.

Table 3

	Monomers and wt. ratio	$[\eta]$	Dissolving solvent	Diluting solvent
Ex.12	$\alpha\text{ClS}/17\text{FMA}/$ $\text{GMA}=50/45/5$	1.0	m-XHF	$\text{CH}_3\text{CCl}_3$
Ex.13	$\alpha\text{ClCH}/19\text{FA}/$ $\text{GMA}=30/66/4$	0.98	$\text{CHCl}_3$	$\text{CCl}_2\text{F}-\text{CClF}_2$
Ex.14	$\alpha\text{FS}/17\text{FMA}/\text{GMA}=$ $45/50/5$	0.89	m-XHF	$\text{CH}_3\text{CCl}_3$
Ex.15	$\alpha\text{ClS}/17\text{FA}/\text{GMA}=$ $70/25/5$	1.31	m-XHF	$\text{CH}_3\text{CCl}_3$
Comp. Ex. 5	$19\text{FMA}/\text{MA}/\text{GMA}=$ $65/30/5$	0.68	m-XHF	$\text{CH}_3\text{CCl}_3$

In Table 3, the monomer representing symbols mean the following monomers.













Table 4

	Contact angle (deg) As prepared/after flexing	
	Water	n-Hexadecane
Example 11	117/102	75/51
" 12	119/105	68/49
" 13	120/99	78/45
" 14	115/100	79/55
" 15	112/98	65/44
Comp.Ex.5	106/71	69/19

Example 16

Into a 3-liter four-necked flask equipped with a stirrer, thermometer, reflux condenser and dropping funnel were placed 1.9 liters of water, 400 g of acetone, 150 g of butyl  $\alpha$ -chloroacrylate, 150 g of 17FMA, 1 g of EGMA and 40 g of an emulsifier (K220, product of Nippon Oils & Fats Co., Ltd.), and oxygen was removed from the system by introducing nitrogen thereinto. The flask was placed into a constant-temperature bath at 65°C. After the mixture was heated to a constant temperature, 0.1 liter of water having dissolved therein 1.6 g of azobisisobutyronitrile hydrochloride was added dropwise to the mixture to start polymerization.

Four hours later, a dispersion was obtained

which contained 12.2 wt.% of solids. A portion of the dispersion was sampled and checked for monomer composition ratio and intrinsic viscosity  $[\eta]$ . The butyl  $\alpha$ -chloro-acrylate/17FMA/EGMA ratio was 49.9/49.8/0.3 by weight  
5 (elementary analysis: 41.7% carbon, 10.9% chlorine and 30.2% fluorine) and the viscosity  $[\eta]$  was 0.50.

The dispersion was diluted with water to a concentration of 0.5 wt.% in a padding container. A polyester fabric was dipped in the padding bath, squeezed  
10 to remove the dilution, then dried at 80°C for 3 minutes and heat-treated at 150°C for 3 minutes to obtain a test specimen.

The specimen was tested for water repellency according to JIS L 1092 and for oil-repellency according  
15 to AATCC 118-1966T. The results were 100 and No.4, respectively.

The same specimen as above was washed under the conditions of bath ratio of 1:50 and temperature of 40°C using a household electric washing machine and a detergent  
20 ("Super-Sabu", product of Kao Co., Ltd., Japan,) then dried in air, lightly ironed at 140°C and subjected to the above two tests with the results 90<sup>-</sup> and No.3, respectively.

#### Comparative Example 6

Polymerization was conducted and a test specimen  
25 was prepared under the same conditions are in Example 16

5 Under the same conditions as in Example 16, the specimen was tested for water repellency and for oil repellency before and after laundry. The water repellency reduced from 100<sup>+</sup> to 70, and the oil repellency from No.3 to No.0.

One gram of the same fluorine-containing copolymer as used in Example 13 was dissolved in m-XHF to a concentration 5 wt.%, and the solution was cast into a dish, 9 cm in diameter, and dried, giving a sheet, 100  $\mu$ m in thickness.

20 Comparative Example 7

A specimen was prepared and tested for rupture strength and elongation in the same manner as in Example 17 except that the fluorine-containing copolymer used in Example 11 was replaced by the polymer used in Comparative Example 5. The results were 0.26 kgf/mm<sup>2</sup> and 450%,

respectively.

D/2951.6


## Claims:

1. A fluorine-containing water- and oil-repellent composition comprising a fluorine-containing polymer which comprises at least 10 mole % of a fluorine-containing acrylate represented by the formula:




wherein X is a fluorine atom or  $-\text{CFX}^1\text{X}^2$  group (wherein  $\text{X}^1$  and  $\text{X}^2$  are the same or different and are each a hydrogen atom or fluorine atom), Y is alkylene having 1 to 3 carbon atoms,  $-\text{CH}_2\text{CH}_2\text{N}(\text{R})\text{SO}_2-$  group (wherein R is alkyl having 1 to 4 carbon atoms) or  $-\text{CH}_2\text{CH}(\text{OZ})\text{CH}_2-$  (wherein Z is a hydrogen atom or acetyl), and Rf is fluoroalkyl having 3 to 21 carbon atoms, or fluoroalkyl having 3 to 21 carbon atoms and 1 to 10 oxygen atoms in its carbon chain (wherein no two oxygen atoms are present adjacent to each other).

2. A composition as defined in claim 1 wherein the group Rf group in the fluorine-containing acrylate represented by the formula (1) is a group represented by the formula:



wherein m is an integer of from 1 to 5, n is 0 or 1, q is an integer of from 1 to 5, and  $\text{Rf}^1$  is a fluorine atom or trifluoromethyl, those represented by the formula



wherein p is an integer of from 0 to 5, and Rf<sup>1</sup> is as defined above, or those represented by the formula:



wherein Ph is phenylene, and Rf<sup>2</sup> is perfluoroalkyl having 5 to 15 carbon atoms.

3. A composition as defined in claim 1 which comprises:

- 10            (i) 10 to 90 mole % of the fluorine-containing acrylate represented by the formula (1), and  
               (ii) 90 to 10 mole % of an ethylenically unsaturated monomer.

4. A composition as defined in claim 3 wherein  
 15            the ethylenically unsaturated monomer is at least one of a monomer represented by the formula:




20            wherein A is a hydrogen atom, chlorine atom or methyl and B is alkyl having 1 to 20 carbon atoms, alicyclic group having 6 to 8 carbon atoms or fluoroalkyl having 1 to 10 carbon atoms; ethylene, propylene, styrene; and  
               (metha)acrylate having vinyl, hydroxyl, carboxyl,  
 25            glycidyl, dialkylamino or trialkoxysilyl.

5. A composition as defined in claim 1 which is in the form of a solution.

6. A composition as defined in claim 1 which is in the form of an aqueous dispersion.


5 7. A fluorine-containing water- and oil-repellent composition comprising a fluorine-containing polymer which comprises

(i) 10 to 90 mole % of a monomer represented by the formula:



wherein  $\text{X}^3$  is a fluorine atom, chlorine atom or  $-\text{CFX}^4\text{X}^5$  group (wherein  $\text{X}^4$  and  $\text{X}^5$  are the same or different and are each a hydrogen atom or fluorine atom), and  $\text{R}^1$  is  
15 alkyl having 1 to 20 carbon atoms, alicyclic group, aromatic group or aralkyl;


(ii) 10 to 80 mole % of a monomer represented by the formula:




wherein  $\text{X}^6$  is a hydrogen atom or methyl, Y is alkylene having 1 to 3 carbon atoms,  $-\text{CH}_2\text{CH}_2\text{N}(\text{R})\text{SO}_2-$  group (wherein R is alkyl having 1 to 4 carbon atoms) or  $-\text{CH}_2\text{CH}(\text{OZ})\text{CH}_2-$  (wherein Z is a hydrogen atom or  
25 acetyl), and  $\text{Rf}^3$  is fluoroalkyl having 3 to 21 carbon

atoms, or fluoroalkyl having 3 to 21 carbon atoms and 1 to 10 oxygen atoms in its carbon chain (wherein no two oxygen atoms are present adjacent to each other); and (iii) 0 to 50 mole % of other copolymerizable ethylenically unsaturated monomer, the combined amount of the monomers (i) to (iii) being 100 mole %.

8. A composition as defined in claim 7 wherein the group  $Rf^3$  in the fluorine-containing acrylate represented by the formula (4) is a group represented by the formula:



wherein m is an integer of from 1 to 5, n is 0 or 1, q is an integer of from 1 to 5, and  $Rf^4$  is a fluorine atom or trifluoromethyl, those represented by the formula



wherein p is an integer of from 0 to 5, and  $Rf^4$  is as defined above, or those represented by the formula:



wherein Ph is phenylene, and  $Rf^5$  is perfluoroalkyl having 5 to 15 carbon atoms.

9. A composition as defined in claim 7 which is in the form of a solution.

10. A composition as defined in claim 7 which is



in the form of an aqueous dispersion.

**DERWENT-ACC-NO:** 1987-336178**DERWENT-WEEK:** 199849*COPYRIGHT 2008 DERWENT INFORMATION LTD*

**TITLE:** Water and oil repellent fluorine contg.  
polymer compsns. derived from fluorine  
contg. acrylate(s) and opt. ethylenically  
unsatd. monomer, impart tough, adherent  
coatings to textiles

**INVENTOR:** INUKAI H; OHMORI A ; OMORI A**PATENT-ASSIGNEE:** DAIKIN IND LTD[DAIK]

**PRIORITY-DATA:** 1986JP-238535 (October 6, 1986) , 1986JP-  
122920 (May 28, 1986) , 1986JP-216854  
(September 12, 1986)

**PATENT-FAMILY:**

<b>PUB-NO</b>	<b>PUB-DATE</b>	<b>LANGUAGE</b>
EP 247489 A	December 2, 1987	EN
JP 63090588 A	April 21, 1988	JA
JP 63099285 A	April 30, 1988	JA
CN 87104448 A	February 24, 1988	ZH
US 5021501 A	June 4, 1991	EN
US 5021527 A	June 4, 1991	EN
JP 92064634 B	October 15, 1992	JA
JP 92076398 B	December 3, 1992	JA
EP 247489 B1	August 25, 1993	EN
DE 3787118 G	September 30, 1993	DE
KR 9511511 B1	October 5, 1995	KO

**DESIGNATED-STATES:** DE FR GB DE FR GB

**APPLICATION-DATA:**

<b>PUB-NO</b>	<b>APPL- DESCRIPTOR</b>	<b>APPL-NO</b>	<b>APPL-DATE</b>
EP 247489A	N/A	1987EP- 107185	May 18, 1987
JP 63099285A	N/A	1986JP- 216854	September 12, 1986
JP 92064634B	N/A	1986JP- 216854	September 12, 1986
JP 63090588A	N/A	1986JP- 238535	October 6, 1986
JP 92076398B	N/A	1986JP- 238535	October 6, 1986
DE 3787118G	N/A	1987DE- 3787118	May 18, 1987
EP 247489B1	N/A	1987EP- 107185	May 18, 1987
KR 9511511B1	N/A	1987KR- 005278	May 27, 1987
US 5021501A	N/A	1989US- 445950	December 11, 1989
US 5021527A	Based on	1989US- 449442	December 11, 1989

**INT-CL-CURRENT:**

<b>TYPE</b>	<b>IPC DATE</b>
CIPP	C08F20/22 20060101
CIPP	C08F220/22 20060101
CIPS	C08F20/10 20060101
CIPS	C08F20/22 20060101
CIPS	C08F20/26 20060101
CIPS	C08F20/38 20060101
CIPS	C08F220/02 20060101
CIPS	C08F220/22 20060101
CIPS	C08F220/28 20060101
CIPS	C08F220/38 20060101
CIPS	C09K3/18 20060101
CIPS	D06M15/277 20060101
CIPS	D06M15/277 20060101

**ABSTRACTED-PUB-NO:** EP 247489 A

### **BASIC-ABSTRACT:**

A fluorine-contg. water- and oil-repellent compsn. comprises a fluorine-contg. polymer which comprises at least 10 mole-%, pref. 10-90 mole-%, of a fluorine-contg. acrylate (I) of formula (I)  $X = F$  or  $-CFX_1X_2$ , ( $X_1$  and  $X_2 = H$  or  $F$ );  $Y = 1-3C$  alkylene,  $-CH_2CH_2N(R)SO_2-$  gp. (in which  $R = 1-4C$  alkyl), or  $-CH_2CH(OZ)CH_2-$  gp. (in which  $Z = H$  or acetyl); and  $R_f = 3-21C$  fluoroalkyl, or  $3-21C$  fluoroalkyl contg. 1-10 O atoms in its C chain (no two O atoms are present adjacent to each other). Opt. included is 90-10 mole-% of an ethylenically unsatd. monomer (II) selected from ethylene, propylene, styrene and (meth)acrylate. A second compsn. comprises 10-90 mole-% of a monomer (III), 10-80 mole-% of a monomer (IV), and 0-50 mole-% of other copolymerisable

ethylenically unsatd. monomer, so that the combined amts. total 100 mole-%. A = H, Cl or methyl; B = 1-20C alkyl, 6-8C alicyclic gp. or 1-10C fluoroalkyl; X3 = F, Cl or -CFX4X5, X4 and X5 = H or F; X6 = H or methyl; R1 = 1-20C alkyl, alicyclic gp., aromatic gp. or aralkyl; Rf3 = Rf.

USE/ADVANTAGE - The compsns. in the form of a soln. or aq. dispersion, impart tough, highly adherent coatings to textile articles such as tents, umbrellas, general clothing, carpets and curtains. The treated articles are resistant to abrasion and durable to laundering.

**TITLE-TERMS:** WATER OIL REPEL FLUORINE CONTAIN  
POLYMER COMPOSITION DERIVATIVE  
ACRYLATE OPTION ETHYLENIC  
UNSATURATED MONOMER IMPART TOUGH  
ADHERE COATING TEXTILE

**DERWENT-CLASS:** A14 A87 F08

**CPI-CODES:** A04-E10D; A04-F06E2; A12-G03; F03-C02; F03-C02A; F04-C; F04-D;

**UNLINKED-DERWENT-REGISTRY-  
NUMBERS:** ; 0272U ; 0398U ;  
0426U ; 0441U

**POLYMER-MULTIPUNCH-CODES-AND-KEY-SERIALS:**

**Key Serials:**

0030 0036 0202 0203 0209 0210 0211  
 0226 0241 0242 0250 0251 0306 0307  
 0495 0496 0502 0503 0509 0510 0514  
 0516 0517 0530 0531 0537 0538 0544  
 0545 0551 0552 0558 0559 0565 0566  
 0572 0573 0579 0580 0586 0587 0593  
 0594 0598 0600 0601 0607 0608 0968  
 0970 0971 1282 1291 1632 1633 2024  
 2066 2085 2093 2108 2116 2122 2123  
 2318 2423 2427 2430 2434 2504 2506  
 2507 2528 2559 2617 2635 2657 2711  
 2723 2763 2819 2822 2845 2857 3048  
 3049 3055 3056 3062 3063 3152 3249  
 3251 3252 3309

**Multipunch Codes:**

02& 05- 062 064 074 079 081 085 086 090  
 143 144 264 265 316 332 347 348 355  
 39& 397 398 42- 431 433 436 440 477 481  
 483 51& 512 53& 532 533 534 535 54&  
 546 551 556 56& 567 573 597 598 600  
 614 619 641 663 664 678 681 688 691  
 720 02& 034 041 046 047 05- 062 064 074  
 079 081 085 086 090 143 144 264 265  
 27& 316 332 348 355 39& 397 398 42-  
 431 433 436 440 477 481 483 51& 512  
 53& 532 533 534 535 54& 546 551 556  
 56& 567 573 597 598 600 614 619 641  
 663 664 678 679 681 691 720 02& 034  
 041 046 05- 050 062 064 074 079 081 085  
 086 090 143 144 264 265 27& 316 332  
 348 355 39& 397 398 42- 431 433 436 440  
 477 481 483 51& 512 53& 532 533 534  
 535 54& 546 551 556 56& 567 573 597  
 598 600 614 619 641 663 664 678 679  
 681 691 720 02& 034 05- 055 056 062 064  
 074 079 081 085 086 090 143 144 264

265 27& 316 332 348 355 39& 397 398  
 42- 431 433 436 440 477 481 483 51& 512  
 53& 532 533 534 535 54& 546 551 556  
 56& 567 573 597 598 600 614 619 641  
 663 664 678 679 681 691 720 02& 034 05-  
 062 064 074 076 077 079 081 085 086  
 090 143 144 157 226 229 264 265 27&  
 316 332 336 348 355 37- 39& 397 398 40-  
 42- 431 433 436 440 477 481 483 51& 512  
 52& 53& 532 533 534 535 54& 546 551  
 556 56& 567 573 59& 597 598 600 614  
 619 641 663 664 678 679 681 691 720  
 02& 034 05- 051 062 064 074 077 078 079  
 081 082 083 084 085 086 090 092 098  
 143 144 145 157 226 264 265 27& 28&  
 316 33- 332 336 348 355 37- 39& 397 398  
 42- 431 433 436 440 477 481 483 51& 512  
 53& 532 533 534 535 54& 546 551 556  
 56& 567 573 59& 597 598 600 614 619  
 641 663 664 678 679 681 691 720 729  
 02& 034 041 046 047 05- 050 055 056 062  
 063 064 074 076 077 078 079 081 085  
 086 090 143 144 157 226 229 264 265  
 28& 316 332 336 348 355 37- 39& 397  
 398 40- 42- 431 433 436 440 477 481 483  
 51& 512 52& 53& 532 533 534 535 54&  
 546 551 556 56& 567 573 597 598 600  
 614 619 641 663 664 678 679 681 691  
 720

## SECONDARY-ACC-NO:

**CPI Secondary Accession Numbers: 1987-143429**